Product Specification Li-Ion Cell 3.7V 3200mAh 3C

(Model No.:INR18650-32E)





1. Scope

This document describes the product specification and using condition of the Lithium-ion Cylindrical rechargeable cell supplied by Akyga battery

2. Product

2.1 Name : Lithium-ion Cylindrical rechargeable cell

2.2 Battery Model: 18650

3. Specification

NO.	Items	Specifications		Remark		
1	Nominal voltage	3. 7	V			
	2.1Nominal capacity	3200	mAh	According to the standard charging after full charge, constant current		
2	2.2Minimum Capacity	3100	mAh	discharge 0.2Cto 2.5V.		
3	Initial Impedance	≤ 145	m Ω	AC Impedance交流内阻 1KHz		
4	Charge Cutoff Voltage	4. 2	V			
5	Discharge Cut-off Voltage	2.50	V			
6	Shipment voltage	3. 5-4. 10	V			
7	Battery weight	\approx 59.0	g			
	8.1Standard Charge	0.2C CC (constant current) charge to 4.2V, then CV (constant voltage 4.2V) charge till charge current decline to 0.02C 0				
8	8.2Standard Discharge	0.2C CC (constant current) discharge to 2.5V				
	8.3Standard testing condition	Temperature :25±2°C; Humidity : ≤85%RH Atmospheric Pressure : 86-106kPa				
9	Max disharge current	3C		Recommended temperature 20-45°C		
10	Operating Temperature	Charge: 10 [~] 45℃				
10		Discharge: -20~50°C				
	Max charge current	10~15°C: 0.2C CCCV	/ to 4.2 V	Charge at very low temperature such as blew 10°C,will be get a lower		
11		15~45°C: 0.5C CCCV	/ to 4.2 V	capacity and reduce cycle life of the battery		
		(-20°C) ~ (0°C) : 0.2C DC to 2.5V				
12	Max Discharge current	$(0^{\circ}C) \sim (25^{\circ}C)$: 0.5C DC to 2.5V				
		(25°C) ~ (50°C) : 3C DC to 2.5V				

a	kyga®
	hatton

NO.	Items	Specifications	Remark
		≤1 months: -20°C ~45°C	a)The capacity for storage shall be $50^{7}75\%$ SOC
13	Storage temperature	≤3 months: -20°C ~35°C	b)The battery should cycle once in June month.Recommended storageTemperature is 25°C of SOC 50°75%.
		≤1 year: -20°C ~25°C	50 15%;
14	Storage Humidity	≪75% RH	



4.2 Basis BOM List/

ltem	Reference	Material name	Model/Specification	Quantity	Remark
1	Cell	18650	3.7V 3200mAh	1	
2	РСМ	ZN-PCM	ZN-PCM DW01+DFN3*3	1	
3	PVC	/	/Blue	1	
4					
5					
6					





6. Visual Inspection/

There shall be no such defect as scratch, flaw, crack, and leakage, which may adversely affect commercial value of the cell.

7. Cell Specification/

7.1 Electrical characteristics

Items	Test Method and Condition Criteria			Criteria		
7.1.1 Initial capacity	The capacity means the discharge capacity of the cell that was discharged to 2.5V with discharge current of 0.2C within one hour after the full charge.			r ≽	3100 mAh	
7.1.2 Cycle life	Cycle life is the capacity of the c full charge and then discharging 0.2C .	ell that was repeated to 2.5V with dis	ated 400 cycles w charge current o	vith f ≥	80% Initial capaci	ity
7.1.3 Initial impedance	Cell resistance was measured at test temperature was 25° C.	: AC 1KHz after 50	% charge and the	e	145 mΩ	
7.1.4 Temperature Capacity Test	The discharge capacity of contra under the condition of normal t table below normal temperature temperature is 0.2C to 2.5 V dis must beyond 3 hours.	ast, under the cor emperature after e and high tempe scharge capacity.t	nditions of differe full charge of the trature to the cap he time betweer	ent temper e battery, pacity of 0. n charging	rature in 25 °C as shown in tl .2 C to 3.0 V, I and dischargi) ow ng
	Charge temperature		Discharge ten	nperature		
		-10 ℃	0 °C	25 °C	C 50	°C
	25 %					C
	25 ℃	≥70%	≥80%	1009	% ≥8	5%



7.2 Mechanical characteristics

Items	Test Method and Condition	Criteria
7.2.1 Vibration Test	Fixed the fully charged cell to vibration table and subjected to vibration cycling that the frequency is to be varied at the rate of 1Hz per minute between 10Hz and 55Hz, the excursion of the vibration is 0.8mm. The cell shall be vibrated for 90 ~100 minutes per axis of XYZ axes.	No explosion No fire, No leakage. 火
7.2.2 Drop Test	The cell was dropped freely from the height of 1000mm to the concrete floor, and each surface was dropped once	No explosion, No fire

7.3 Safety

Items	Items Test Method and Condition	
7.3.1 Crush Test	The pressure on the surface of the fully charged cell do not stop being raised until 17.2 Mpa when the cell is crushed by two flat surfaces.(Max13kN)	No explosion, No fire.
7.3.2 Heating	After full charging at 0.1C, put the battery in the baking oven and start , the temperature of the oven is to be raised at a rate of 5° per minute to a temperature of $130\pm2^{\circ}$, remain for 10minutes at that temperature fl \mathbb{H}	
7.3.3 Short-Circuit Test	After full charge, the positive and negative polarities are connected together by a copper wire whose resistance is less than or equal to $80\pm20m\Omega$.	No explosion, No fire .
7.3.4 Over-charge Test	The cell is overcharged to 4.6V with a current of 3C and holded for 8 hours.	

	akyga	
8.	Standard environmental Unless otherwise specifi Temperature: 25±2℃	l test condition ied, all tests stated in this Product Specification are conducted at below condition. Relative humidity: 65±20%
9.	Charging Charging current and char The charger shall be desi It is dangerous that char electrical,mechanical sat	arging voltage should be less than specified in the Product Specification. igned to comply with Product Specification. ging with higher current or voltage than Product Specification may cause damage to the cell fety performance.
10.	warranty Period of warranty:	12 months after sales;
	Range of warranty:	There is low voltage, expansion or leakage with the correct use of the cell in the period of warranty.
11.	Liability	
	Please use the Lithium-ic under the product specif the safety unless the cell	on Polymer rechargeable cells supplied by Akyga battery fication .It may cause fire or expansion if the cells are used incorrect .We will not guarantee is are used under the product specification.
12.	Identification Warnings would better b *Using the charger desig *Don't throw the battery *Don't short-circuit . *Don't unpack the batter	be marked on the surface of the battery which is tied up by certain cells: inated by the manufacturer. y in fire or heat it . ry or change its structure.



13. Notice for Designing Battery Pack

13.1 Battery Pack design

13.1.1 Battery shell should be with enough mechanical strength, to protect the inner cell from mechanical shock;

13.1.2 No cell movement in the battery pack should be allowed;

13.1.3 No Sharp edge or bulge components should be inside the pack containing the battery;

13.2 Avoid some components to contact the edge of packing foil of batteries ;

13.3 Tab connection

13.3.1 Ultrasonic welding or spot welding is recommended to connect battery with PCM or other parts;

13.3.2 The tab is not very firm. Don't bend the tab o especially the positive pole. It will rupture easily;

13.3.3 If apply manual solder method to connect tab with PCM, below notice is very important to ensure battery performance:

1). The solder iron should be temperature controlled and ESD safe;

2). The soldering iron temperature should be 360-420°C;

3). Soldering time should not be longer than 3s;

4). Soldering times should not exceed 3 times ,secondary welding should be done after the poles are cooling;

5). Directly heat cell body is strictly prohibited;

6). Don't let the electric iron contact the surface of the cell.

Please use the battery according to the provisions as below ,Incorrect using of the battery may cause fire or expansion, and destroy its performance.

- 14.1 Don't throw the cell in fire or heat it or store it in high temperature place ;
- 14.2 Don't operate or use the cell under high temperature or next to the heating material. Don't throw the cell in fire or heat it;
- 14.3. Don't fix the positive and negative of the cell reversely to the electrical equipment ;
- 14.4 Don't connect the positive and negative polarities by metallic conductor such as a metallic wire;
- 14.5 Don't impact or scrape the surface of the cell by spiculate parts;
- 14.6 Don't stab it with a needle, beating, treading, fold or other way;
- 14.7 Don't drop or fling the cell randomly;
- 14.8 Keep the cell sealed!(Don't open or deform folding edge,Don't bend or fold sealing edge,etc);
- 14.9 Don t unpack the battery or change its structure!;
- 14.10 Don't throw the cell in water, please keep it from humidity.



15.Attention

15.1 Please use the qualified equipment for charging and recharging the cell;

15.2 Don't use different type of cells supplied by different manufacturer together;

15.3 Don't charge the heating or modification cell;

15.4 Don't let the cell over-discharge.

16.1Reminding

- 16.1 Don't use the damaged cells (the sealing edge was damaged, the pack was damaged, the electrolyte leakage, etc.). If the cell heating when using, go far away from the cell, it may avoid unnecessary damage;
- 16.2 Theoretically, there is not flowing electrolyte in the cell, but if the leakage of electrolyte happen, or the electrolyte splash down to the skin, eyes or other parts of the body, wash with water and go to hospital immediately;
- 16.3 The cells supplied by Akyga battery had passed the QC before sales, If there is any abnormal problem such as unidentified heating, expansion and peculiar smell, please contact with us;

16.4 The Pack stored beyond half year should be charged to $3.7^{3.9V}$ /cell with constant current at 0.5C.